


Name: _____ [printed]

“On my honor, as an Aggie, I have neither given nor received unauthorized aid on this academic work.”


_____ [signature]

Final Exam, May 3, 2013, 100 pts
Polymer Chemistry, CHEM 466, Spring 2013
Texas A&M University, College Station, TX, USA

1. The copolyimide shown below was reported recently¹ to exhibit tunable optical and electronic properties through charge transfer between the AMTPA and NTCDI units. Memory devices constructed from a series of these copolymers, with variation in the x value, gave a change from “volatile dynamic random access memory to nonvolatile write once read many memory characteristics as the NTCDI composition increased”.




- (a) Provide a retrosynthetic pathway by which this copolymer structure could be prepared. To avoid confusion, please note that the 6-membered ring imides are part of the NTCDI monomer, which is shown below. **[10 points]**



¹ Kurosawa, T.; Lai, Y.-C.; Yu, A.-D.; Wu, H.-C.; Higashihara, T.; Ueda, M.; Chen, W.-C. Effects of the Acceptor Conjugation Length and Composition on the Electrical Memory Characteristics of Random Copolyimides”, *J. Polym. Sci, Part A: Polym. Chem.* **2013**, *51*, 1348-1358.

Name: _____ [printed]


- (b) State whether this copolyimide is a random/statistical copolymer or a block copolymer. **[2 points]**
- (c) State whether the polymerization step of your retrosynthesis would proceed by a chain-growth or step-growth process. **[2 points]**
- (d) State whether your polymerization would be controlled or un-controlled. **[2 points]**
- (e) State whether the molecular weight distribution would be expected to be narrow or broad. **[2 points]**
- (f) Draw the expected DP_n vs. % monomer conversion plot on the axes below. **[4 points]**





- (g) Predict the thermal characteristics for this polymer, in terms of thermal transition temperature(s) and thermal decomposition temperature(s), and explain. **[4 points]**

2. As promised during lecture, this question requires that you provide a retrosynthetic analysis for the following molecular brush, which is prepared by a combination of RAFT polymerization and ROMP. Please note a few points: i) the termination step was not shown explicitly during the discussion of this molecular brush, but was illustrated during the final lecture of the course; ii) the chemical structure for N-phenylmaleimide is given and may be of use; iii) although the mechanism for RAFT polymerization was illustrated during lecture for a trithiocarbonate chain transfer agent, the mechanism is the same for the dithioester functionality.

(a) Provide a retrosynthetic pathway for the preparation of this molecular brush (your answer can continue onto the next page). **[15 points]**



$$x = y = 0.5$$



N-phenylmaleimide

Name: _____ [printed]

- (b) Given that $x = y = 0.5$ and the styrene and N-phenylmaleimide units are alternating for the copolymer graft, predict the reactivity ratio values for the copolymerization of *p*-hydroxystyrene (1) and N-phenylmaleimide (2). **[2 points]**


$r_1 =$

$r_2 =$

Name: _____ [printed]

- (c) Choose one of your RAFT polymerization steps and draw the electron arrow-pushing mechanism for the RAFT polymerization, labeling all initiation, propagation and (reversible) termination steps. **[6 points]**

3. For the following cationic chain-growth, addition copolymerization:






(a) Provide the products. **[10 points]**

(b) State which regioisomer for the isoprene repeat units is favored, and state and illustrate mechanistically the reason for your answer. **[5 points]**

(c) State at least one product in which this copolymer could be found, e.g. name the item that was shown during lecture. **[2 points]**

4. (a) For the following polypropylene segments, label their tacticities and predict whether they are likely to pack into crystalline or amorphous domains. **[12 points]**



(b) Describe the key features of the system that we discussed as being used by Dow to obtain olefin block copolymers with alternating semicrystalline and amorphous segments. **[6 points]**

Name: _____ [printed]

5. For quiz #10, several students expressed interest in the broad range of applications for super glue, including those beyond typical daily applications, *e.g.* in the medical field, forensics, *etc.*, and requested that a final examination question involve super glue. Therefore,
- (a) provide the chemistry for any version of an α -cyanoacrylate “super glue”, including the monomer, initiator, mechanism of polymerization and the final polymer product structure; **[12 points]**
- (b) state what kind of polymerization is involved; **[2 points]**
- (c) state why this polymerization does not proceed while the monomer is stored in a closed tube. **[2 points]**

Equations, which may be of use:

Number-average molecular weight:

$$M_n = \frac{\sum N_x M_x}{\sum N_x}$$

 $N_x = \# \text{ moles of polymer chains having molecular weight, } M_x$

Weight-average molecular weight:

$$M_w = \sum w_x M_x = \frac{\sum N_x M_x^2}{\sum N_x M_x}$$

 $w_x = \text{wt fraction of polymer chains having molecular weight, } M_x = \frac{N_x M_x}{\sum N_x M_x}$

Degree of polymerization:

$$DP_n = \frac{1}{1 - c}$$

 $c = \text{extent of conversion of functional groups}$

$$DP_n = \frac{[\text{monomer}]_0 \cdot \% \text{ monomer conversion}}{[\text{initiator}]_0 \cdot f}$$

Polydispersity index:

$$PDI = \frac{M_w}{M_n}$$

Critical extent of reaction:

$$p_c = \frac{2}{f_{av}}$$

Average degree of monomer functionality:

$$f_{av} = \frac{\sum N_i f_i}{\sum N_i}$$

Textbook:

Hiemenz, P. C.; Lodge, T. P. *Polymer Chemistry*, 2nd Edition; CRC Press, Taylor & Francis Group: Boca Raton, FL, USA, 2007