


Name: _____ [printed]

“On my honor, as an Aggie, I have neither given nor received
unauthorized aid on this academic work.”

_____ [signature]

Exam IV, April 21, 2011, 125 pts
Polymer Chemistry, CHEM 466, Spring 2011
Texas A&M University, College Station, TX, USA

1. For the following atom transfer radical polymerization of styrene in anisole, initiated by α -bromoethylbenzene, and using CuBr and *N,N,N',N'',N''*-pentamethyldiethylenetriamine (PMDETA) as the catalyst/ligand system:



- (a) Give the full structure for the polymer product (draw above). **[10 points]**
- (b) Calculate the initiator efficiency, given that the initial monomer concentration is 0.1 mol/L, the initial concentrations of α -bromoethylbenzene and CuBr are 0.001 mol/L each (with an excess of PMDETA ligand), and ^1H NMR data indicate an integration value of 500 for the 5 overlapping phenyl protons of the initiator, monomer and polymer repeat units (anisole removed), and an integration value of 60 for the combined 3 vinylic protons of the unreacted monomer. **[10 points]**
- (c) Insert the calculated value for the degree of polymerization onto your structure for part (a). **[5 points]**


Name: _____ [printed]

- (d) Draw the electron arrow-pushing mechanisms and give the polymer products that would occur from terminations by radical coupling and disproportionation.

Radical coupling [5 points]

Disproportionation [5 points]


- (e) Why are irreversible termination and chain transfer reactions limited for this polymerization of styrene, in comparison to polymerization of styrene initiated by azobisisobutyronitrile (AIBN)? [5 points]
- (f) On the axes below, draw the growth profiles of DP_n vs. % monomer conversion that would be expected for this controlled ATRP of styrene and traditional styrene polymerization using AIBN (don't forget to label the axes and your plots). [5 points]




- (g) If the DP_n calculated under part (b) was too large, how could it be reduced by this ATRP method? [5 points]
- (h) How could the DP_n be reduced during the traditional AIBN-initiated polymerization? [5 points]

Name: _____ [printed]

2. During our first class lecture, we discussed supramolecular polymer materials as described in Folmer, B. J. B.; Sijbesma, R. P.; Versteegen, R. M.; van der Rijt, J. A. J.; Meijer, E. W. *Adv. Mater.* **2000**, 12(12), 874-878, and you were told that, by the end of the semester, you would be able to propose synthetic routes to produce each of the supramolecular polymer systems reported. Provide a retrosynthetic approach to the following structure, **3**. A few hints: Work backwards from the final structure (**3**, given below); look for parts of **3** and the exact polymer structure (-O-X-O-) that you recognize; hydrogenation of an initially prepared analog of the HO-X-OH polymer is involved. **[20 points]**




Where the -O-X-O- unit is derived from:



Name: _____ [printed]

2. (cont'd.)

3. During our discussion of the article Kobayashi, S.; Lu, C.; Hoyer, T. R.; Hillmyer, M. A. *J. Am. Chem. Soc.* **2009**, *131*, 7960-7961, the limited degree of polymerization ($DP_n \sim 10$) obtained by traditional azobisisobutyronitrile (AIBN)-initiated radical polymerization of the cyclic diene 3-methylenecyclopentene was mentioned.



- (a) Provide the electron arrow-pushing mechanistic steps for **initiation** and **propagation** to give the polymer having 4,3- and 1,4-regiochemistries (please note, the numbering for the nomenclature of the monomer (3-methylenecyclopentene) is opposite to the numbering of the monomer diene and the resulting repeat units), label the steps, show resonance structures, and show the chemical structure for the polymer. **[20 points]**

Name: _____ [printed]

- (b) It is likely that chain-transfer (CT) reactions to monomer are responsible for the limited DP_n . Provide an electron arrow-pushing mechanism for CT to monomer that leads to a resonance-stabilized radical species, showing the resonance structures to explain why the CT reaction might be prevalent. **[20 points]**

- (c) Given the stated prevalence of CT to monomer, include the appropriate chain end on your structure for part (a). **[5 points]**
- (d) Do you predict that this monomer has a relatively high or low chain transfer constant? **[5 points]**

Equations, which may be of use:

Number-average molecular weight:

$$M_n = \frac{\sum N_x M_x}{\sum N_x}$$

N_x = # moles of polymer chains having molecular weight, M_x

Weight-average molecular weight:

$$M_w = \sum w_x M_x = \frac{\sum N_x M_x^2}{\sum N_x M_x}$$

w_x = wt fraction of polymer chains having molecular weight, $M_x = \frac{N_x M_x}{\sum N_x M_x}$

Degree of polymerization:

$$DP_n = \frac{1}{1 - c}$$

c = extent of conversion of functional groups

$$DP_n = \frac{[\text{monomer}]_0 \cdot \% \text{ monomer conversion}}{[\text{initiator}]_0 \cdot f}$$

Polydispersity index:

$$PDI = \frac{M_w}{M_n}$$

Critical extent of reaction:

$$p_c = \frac{2}{f_{av}}$$

Average degree of monomer functionality:

$$f_{av} = \frac{\sum N_i f_i}{\sum N_i}$$

Textbook:

Hiemenz, P. C.; Lodge, T. P. *Polymer Chemistry*, 2nd Edition; CRC Press, Taylor & Francis Group: Boca Raton, FL, USA, 2007